

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B24D 3/28, 11/00	A1	(11) International Publication Number: WO 96/39278 (43) International Publication Date: 12 December 1996 (12.12.96)
(21) International Application Number: PCT/US96/06198 (22) International Filing Date: 2 May 1996 (02.05.96) (30) Priority Data: 08/469,286 6 June 1995 (06.06.95) US (71) Applicant: NORTON COMPANY [US/US]; 1 New Bond Street, P.O. Box 15138, Worcester, MA 01615-0138 (US). (72) Inventors: SWEL, Gwo, Shin; 8430 Avonside Drive, East Amherst, NY 14051 (US). GAETA, Anthony, C.; 3789 Ridge Road, Rockport, NY 14094 (US). YANG, Wen, Liang, Patrick; 8 Birch Hill Road, Ballston Lake, NY 12019 (US). CERCENA, Jane, L.; 139 Ashford Center Road, Ashford, CT 02678 (US). (74) Agents: BENNETT, David et al.; Saint Gobain Corporation, 1 New Bond Street, P.O. Box 15138, Worcester, MA 01615-0138 (US).		(81) Designated States: AU, BR, CA, JP, MX, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: DUAL CURE BINDER SYSTEMS (57) Abstract A coated abrasives having very desirable efficiencies in production is provided by the use of a binder coat which comprises a compound having at least one function that is radiation curable and at least one function that is polymerizable under thermally activated conditions.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

WO 96/39278

PCT/US96/06198

DUAL CURE BINDER SYSTEMSBackground of the Invention

5 This invention relates to a process for the
production of coated abrasives using a novel dual-curing
binder system.

10 In the conventional production of coated abrasives,
a backing material is coated with a first resin coat,
known as a maker coat, and a layer of abrasive particles
are deposited thereon either by gravity coating or by an
electrostatic projection, ("UP"), process. The function
of the maker coat is to act as a primary anchor firmly
bonding the grits to the backing. This maker coat is
cured to ensure that the bond is firm before the main
15 coating that holds the grits rigidly during grinding is
applied. This is known as the size coat. The size coat
is then cured, and occasionally a supersize coat is
applied over the top to provide a grinding aid, anti-
static additive or other adjuvant close to the point at
20 which the coated abrasive contacts the surface to be
ground when in use.

For many years phenolic resins have been the
preferred component of the size coat on account of their
excellent physical properties. They have also been
25 preferred as the maker coat, partly because of their
excellent adhesion to conventional backing materials and
phenolic size coats. By using such similar binder coats
it is possible to partially cure the maker and complete
the cure at the same time as the cure of the size coat.
30 Phenolics are also popular because they are cheap and
because they are applied in an aqueous solution such that
no organic solvents that need to be recycled or disposed
of in an environmentally acceptable manner are involved.

Phenolic resins have drawbacks however, including
35 the need to remove water before cure is initiated. In
addition the prolonged heating required to complete a
uniform cure without blistering often lasts many hours.
The process of curing is usually operated in a continuous
mode wherein a coated abrasive sheet many meters in

WO 96/39278

PCT/US96/06198

length is fed slowly into long ovens. The ovens in which the cure occurs are called festoon ovens and the product to be cured is draped in long folds over support slats and these folds move at a pre-determined rate through the oven. The supports over which the sheet is folded often cause defects on the back of the sheet and a misorientation of the grain in the other surface where the maker resin is receiving the initial cure.

For this reason there have been many suggestions for replacement of phenolic resins by other binder products.

It has been proposed for example, to use acrylate resins, urea-formaldehyde resins, polyurethane resins, polyester resins, melamine resins, epoxy resins, and alkyd resins.

Some of these are curable by radiation treatment such as by the use of UV light or electron beam radiation. These can be quite expensive and have limitations on the amount of conventional filler material because the particles can prevent effective cure of the parts of the resin binder in the "shadows" behind the particles where little or no radiation penetrates. UV cure radiation has a quite shallow depth of cure in most situations in fact. Electron beam radiation has greater depth of cure but if the dosage is large, the backing material may be deteriorated, leading to premature product failure.

The other binders proposed, while often being well-adapted to specialized uses such as lightweight or waterproof abrasives or very fine grit abrasive products, in general do not provide sufficient strength and efficiency to displace the versatile phenolic resins that are used in the greatest number of coated abrasive products.

A binder formulation has now been discovered that is extremely versatile and effective, particularly when used as a maker coat and the present invention provides a process for making coated abrasive using such a binder.

General Description of the Invention

WO 96/39278

PCT/US96/06198

According to a first aspect of this invention there is provided for the production of a coated abrasive comprising:

- 5 a. Forming an abrasive layer on a backing material, said abrasive layer comprising abrasive grits and a bi-functional binder formulation comprising a compound having at least one radiation-curable function and at least one thermally curable function per
10 molecule;
2. Using radiation to at least partially cure the radiation-curable functions; and
- 3 Subsequently completing the cure by activation of the thermally curable functions.

15 The binder component is described being "bi-functional" and by this intended that the binder contain two different types of functional groups that cure by different mechanisms. It is however contemplated the each molecule of binder may have more than one, for
20 example from 1 to 3 or even more of each type of functional group. Preferred binders however have one of both kinds of functional group.

According to a further aspect of this invention, the partial cure of the bi-functional binder is followed by
25 deposition of a phenolic size coat which is then thermally cured at the same time as the cure of the bi-functional binder is completed.

A further aspect of the invention is the use of a maker coat that comprises a bi-functional compound having
30 at least one radiation-curable function and at least one thermally-curable function, wherein the compound is a liquid in the uncured state. Since the maker is itself a liquid, no solvent need be removed before curing can be initiated, thus greatly accelerating the curing process.

35 Such formulations are referred to as having 100% solids, indicating thereby that no weight is lost upon cure.

In a further embodiment of the invention the binder layer comprising the bifunctional component may be applied as a size coat, that is, over the top of a layer

WO 96/39278

PCT/US96/06198

of abrasive particles adhered to the backing by means of a conventional maker resin layer, (such as a phenolic resin maker coat), or over a maker coat that also comprises a bi-functional binder component.

- 5 The bi-functional compound comprises at least one and often as many as three or more radiation-curable functions, by which is meant groups that react with similar groups when activated by radiation such as UV light or an electron beam. The reaction may be initiated
- 10 by free-radical or cationic initiation and of course different species of initiators or promoters are applicable in each case. Typical radiation-curable functions include unsaturated groups such as vinyl, acrylates, methacrylates, ethacrylates, cycloaliphatic
- 15 epoxides and the like. The preferred UV-curable functions are acrylate groups. Where the bi-functional compound comprised a single UV-curable group, it may be desirable to incorporate a minor amount of a further compound containing groups reactive with the UV-curable
- 20 group such di-acrylates, tri-acrylates and N-vinylpyrrolidone. Suitable reactive diluents include trimethylol propane triacrylate, (TMPTA); triethylene glycol diacrylate (TRPGDA); hexane diol-diacrylate, (HDODA); tetraethylene glycol diacrylate, (TEGDA); N-
- 25 vinyl pyrrolidone (NVP) and mixtures thereof. Such additives are very effective in adjusting initial viscosity and determining the flexibility of the cured formulation. They may be added in amounts up to about 50% by weight. This permits control over the formulation
- 30 viscosity, the degree of cure and the physical properties of the partially cured bi-functional compound. In addition it is preferred that such added reactive compounds be liquid or soluble in the mixture as to add no solvent that needs to be removed prior to cure.
- 35 Cure by means of UV radiation is usually sufficient to ensure adequate retention of the abrasive grains during subsequent processing before curing of the thermally curable functions is completed.

WO 96/39278

PCT/US96/06198

The thermally-curable function may be provided for example by epoxy groups, amine groups, urethanes or unsaturated polyesters. The preferred thermally curable function is however the epoxy group since this will
5 result in a plurality of terminal hydroxyl groups on the cured binder which would ensure that a size coat deposited thereon and comprising a resin that will react with the epoxy group such as phenolics, urea/formaldehyde resins and epoxy resins would bond firmly thereto, so
10 decreasing the risk of de-lamination during use.

Cure of the thermally-curable functions is preferably accelerated or promoted by the addition of known catalysts such as peroxides or 2-methyl-imidazole.

The backbone of the bifunctional binder is not
15 critical beyond providing a stable, essentially non-reactive support for the functional groups that does not interfere with the cure reactions. A suitable backbone is based on a bisphenol derivative such as bisphenol A or bisphenol E. Other possible backbones may be provided by
20 novolacs, urethanes, epoxy-novolacs and polyesters.

These backbone compounds can be reacted by known techniques to form terminal epoxide groups which are of course thermally curable. Such epoxidized backbone materials are well-known. To obtain the bi-functional
25 binder components of the invention this epoxidized derivative is then reacted with a compound containing a function that is reactable with the epoxide function and also contains a radiation-curable function. The amount of the compound added is less than the stoichiometric
30 amount that is required to react with all the epoxide functions present in the molecule. A typical compound may contain an acrylic or methacrylic group and an active-hydrogen containing group, and suitable examples include acrylic and methacrylic acids. The active
35 hydrogen-containing group reacts with the epoxide group, replacing that (thermally-curable) functionality with a (radiation-curable) (meth)acrylate functionality.

The relative amounts of the epoxidized backbone and the radiation curable compound are important in that they

WO 96/39278

PCT/US96/06198

control the relative degrees of curing that can occur in the radiation and thermal curing phases of the complete cure of the bi-functional binder compound. Usually the ratio of thermally curable groups to radiation-curable groups in the bifunctional binder is from 1:2 to 2:1 and most preferably about 1:1.

Detailed Description of the Invention

The bi-functional binder composition can be applied directly to the backing and then receive a coating of the abrasive grit. Alternatively a mixture of the grit and binder can be made and this mixture is then applied directly to the backing material. This is most frequently done when the abrasive grit is very fine and the application for which the coated abrasive is intended in a fining or finishing application. In such situations a subsequent size coat application may be unnecessary.

The binder composition can additionally contain catalysts or activators designed to initiate or accelerate the radiation or thermal cure operations. It can also include filler materials. It is however, preferred that such fillers do not interfere with the radiation curing whether because of the amount or size of the particles or because the material is essentially UV transparent much as aluminum tri-hydrate. Fillers may often be treated with a coupling agent such as a silane which results in improved adhesion between the filler and the binder so as to increase the dispersion and retention of the filler in the formulation. Addition of fillers is very effective to reduce the cost of the binder system and at the same time increase the physical strength of the cured binder layer. The addition of a filler treated with a coupling agent is therefore a preferred feature of the binder formulations according to the invention.

A preferred bifunctional binder formulation component is an epoxy-acrylate with a bisphenol A backbone reacted at each end to provide epoxy groups, one of which is then acrylated by reaction with acrylic acid.

A resin of this description is available from UCB Chemicals under the registered trademark Ebecryl 3605.

WO 96/39278

PCT/US96/06198

The above bifunctional binder, (styled hereafter "3605"), was evaluated in a number of experiments to determine the extent of cure measured by the amount of heat evolved, (Joules/g), by either differential photo calorimetry, (for the UV cure), or differential scanning calorimetry, (for thermal cure). In each case the glass transition temperature, (Tg), is measured. This to indicates the degree of cure attained, with higher Tg values equated to higher degrees of cure.

- 10 The same amount of 3605 was used in each case and the amount (if any) of initiator or catalyst is indicated. The additives used were:
- Darocure 1173, (a free radical photo initiator of UV Cure available from Ciba-Geigy);
- 15 Cyracure UV1-6974, (a cationic photo initiator of UV cure available from Union Carbide Corporation);
- 2MI (2-methyimidazole which is a thermal cure initiator); and
- TBHP (t-butyl hydroperoxide which is an initiator of
- 20 thermal cure).
- In most cases an additional thermal cure was applied to complete the cure. The Tg at each stage was measured.

Cure Mode/ Additive	Heat Generated (J/g)	Tg(°C)	Tg after added Ther. Cure (°C)
UV/3% 1173	152.6	23.38	27.97
Therm./2% TBHP	254	31.98	34.46
UV/4% 6974	130.9	24.81	71.1
Thermal/2% 2MI	93.95	24.78	—
UV/3% 1173 + 2% 6974	163.4 (UV)	35.34	91.91
UV + Thermal/ 3% 1173+2% 2MI	126.7 (UV) 42.84 (Thermal)	45.98	55.29
*Thermal + UV/ 2% 2MI+3% 1173	98.44 (Thermal) 0.7 (UV)	19.15	25.66

WO 96/39278

PCT/US96/06198

* If the cure of the thermally polymerizable groups precedes that of the UV curable groups, the latter polymerization is significantly inhibited and retarded.

5 For this reason the reverse order of activation is usually preferred.

It will be noted that the addition of a subsequent thermal cure operation after the bi-functional binder functions have been cured resulted in enhanced properties
10 and this is a preferred feature of the present invention.

To save expense, the binder formulation according to the invention, when applied as a maker coat, can be pattern-coated on the backing such that when abrasive grits are applied to the backing material, they adhere
15 only to the binder in the applied pattern. Because the binder can then be radiation-cured in seconds, the grain is retained in place and a size applied over the top will penetrate between the grains and bond directly to the backing. This is particularly advantageous if the size
20 coat is a phenolic resin and the backing is of a hydrophilic nature such that the phenolic resin bonds readily thereto. It may also be desirable to incorporate reactive fillers into such size coating so as to ensure optimum placement at all stages during the grinding.

25 Description of Specific Embodiments

The invention is now described with reference to specific formulations. These are not however to be understood as implying any limitation on the essential scope of the invention.

30 A typical fiber-backed abrasive disc using fused alumina/zirconia grits and phenolic maker and size coats were duplicated with the difference that a binder formulation according to the invention was substituted for the phenolic maker coat.

35 The binder formulation had the composition;

Reactants: 3605 (bifunctional binder)	80% by wt.
N-vinylpyrrolidone	20% by wt.
Additives: 2MI (Initiator)	1% of reactants wt.
1173 (Initiator)	3% of reactant wt.

WO 96/39278

PCT/US96/06198

 $\text{Al}(\text{OH})_3$ (7.5m)

50% of reactant wt.

The grit sizes used were 80 grit.

The binder formulation was applied at about 267 g/m^2 , (18 lbs/ream). The samples were UP-coated with grit at 178

5 g/m^2 , (12 lbs/ream). Two sheets were produced.

The samples were cured using UV light, (set on "high", with a speed of passage under the light source of 3.05 m/min., (10 ft/minute), with each sheet given two passages to ensure complete cure.

10 The sheet samples with maker coats as described above were then treated with a commercial phenolic size coat at an add-on weight of 207 g/m^2 , (14 lbs/ream).

Both sheets were then cured as follows:

1 hour at 65.6°C (150°F);

15 1 hour at 79.4°C (175°F); and

16 hours at 107.2°C (225°F).

7" discs were cut from these sheets and tested by angle grinding on the edge of a 3.18 mm, (one eighth inch), thick bar of C-1018 steel.

20 The disc was supported on a pad and urged against the steel bar at 3.64 kg or 2.73 kg; (8 lbs or 6 lbs respectively) at an angle of 15° or 10° respectively and moved relative to the bar. The time of contact in each case was 30 seconds. The weight loss of the disc and the
25 bar were measured after each contact and after each contact the condition of the edge was examined. The results were as follows:

WO 96/39278

PCT/US96/06198

Sample #	Contact	Disc 1st Change	Bar at change	Ratio	Comments on Edge
1 (15° angle, 8 lb weight), Hand pad backing	1	0.99g.	11.34g.	11.45	Acceptable
	2	0.30g.	12.15g.	40.50	Acceptable
	3	0.15	10.52	70.13	Acceptable (New Bar)
	4	0.16	10.88	68.00	Acceptable
2 (10° angle, 6 lb. wt. Soft pad backing)	1	0.83	12.20	14.70	Not very good
	2	0.20	9.97	49.85	Acceptable
	3	0.07	10.17	145.29	Acceptable (New Bar)
	4	0.04	9.65	241.25	Acceptable (New Bar)

The performance of the discs was comparable to that of commercial all-phenolic binder discs. It was
 5 noticeable that the phenolic size coat adhered extremely well to the maker coat according to the invention.

WO 96/39278

PCT/US96/06198

Claims

1. A process for the production of a coated abrasive which comprises
 - a. Forming an abrasive layer on a backing material, said abrasive layer comprising abrasive grits and a bi-functional binder formulation which comprises a compound having at least one radiation-curable function and at least one thermally curable function per molecule;
 - b. Using radiation to at least partially cure the radiation-curable functions; and
 - c. Subsequently completing the cure by activation of the thermally curable functions.
2. A process according to Claim 1 in which the bi-functional binder formulation comprises both UV-curable and thermally curable functions.
3. A process according to Claim 1 in which the radiation-curable functions are acrylate, methacrylate or cycloaliphatic epoxy groups .
4. A process according to Claim 1 in which the thermally-curable functions are epoxy groups.
5. A process according to Claim 1 in which the bi-functional binder composition is applied as a maker coat and the abrasive grits are deposited thereon.
6. A process according to Claim 5 in which the bi-functional binder composition is pattern-coated on the backing material.
7. A process according to Claim 1 in which the bifunctional binder composition is added as a component of a size coat.
8. A process according to Claim 1 in which a size coat comprising a resin having groups reactable with the bi-functional binder is applied over the abrasive layer.
9. A process according to Claim 8 in which the size coat comprises a phenolic resin.
10. A process according to Claim 8 in which the size coat is cured at the same time as the thermally

WO 96/39278

PCT/US96/06198

- curable function of the bi-functional binder formulation.
11. A process according to Claim 1 in which the bi-functional binder formulation is 100% solids.
- 5 12. A process according to Claim 1 in which the bi-functional binder formulation comprises additional monomers or oligomers containing one or more groups copolymerizable with the radiation-polymerizable functions of the bi-functional compound.
- 10 13. A process according to Claim 1 in which the bi-functional binder formulation also comprises a filler.
14. A process according to Claim 13 in which the filler has been surface treated with a coupling agent to
- 15 increase its compatibility with the binder.
15. A process according to Claim 1 in which, after the cure of the bi-functional binder component is essentially complete, the coated abrasive product is subjected to a further thermal cure operation.
- 20 16. A process for the production of a coated abrasive which comprises:
- a. Coating a backing layer with a maker formulation comprising a compound having at least one UV-curable (meth)acrylate group and at least one
- 25 thermally-curable epoxy group;
- b. Applying a layer of abrasive grits to the maker formulation;
- c. Exposing the maker coat to UV radiation sufficient to at lease partially cure the UV-curable
- 30 (meth)acrylate groups; and
- d. Subsequently curing the epoxy groups.
17. A process according to Claim 16 in which the maker formulation comprises other groups copolymerizable with the (meth)acrylate groups.
- 35 18. A process according to Claim 16 in which the maker coat is 100% solids.
19. A process according to Claim 16 in which a phenolic size coat is applied over the abrasive process and

WO 96/39278

PCT/US96/06198

- is cured at the same time as the thermally curable functions of the maker coat.
20. A process according to Claim 16 in which the maker formulation is pattern-coated on the backing material.
21. A process according to Claim 16 in which the coated abrasive is subjected to a thermal cure operation after the cure of the bi-functional binder component is essentially complete.
22. A process according to Claim 16 in which the bi-functional binder formulation also comprises a filler that has been surface modified by reaction with a silane.
23. A binder formulation for use in manufacturing coated abrasive comprising an epoxy-acrylate with a bisphenol A backbone reacted at each end to provide epoxy groups, one of which is then acrylated by reaction with acrylic acid.
24. A binder formulation according to Claim 23 which further comprises compounds copolymerizable with the radiation-curable acrylate groups.
25. A binder formulation according to Claim 23 which is 100% solids.
26. A binder formulation according to Claim 23 in which the bi-functional compound comprises at least one each of (meth)acrylate and epoxy groups.
27. A binder formulation according to Claim 23 which further comprises a filler.
28. A binder formulation according to Claim 27 in which the filler has been silane-modified.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 96/06198

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B24D3/28 B24D11/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 B24D C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>WO,A,94 04318 (MINNESOTA MINING AND MANUFACTURING COMPANY) 3 March 1994</p> <p>see the whole document see specially claims 1,7-9,11; and very specially claims 17,21,23,27 --- -/-</p>	<p>1-5, 7-13, 15-19, 21,23-27</p>

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

21 August 1996

Date of mailing of the international search report

04.09.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Molto Pinol, F.

INTERNATIONAL SEARCH REPORT

Int. Application No
PCT/US 96/06198

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB,A,2 087 263 (KENNECOTT CORPORATION) 26 May 1982 see page 1, line 5 - line 37 see page 1, line 63 - page 2, line 10 see page 3, line 29 see page 4, line 31 see example 2,4,5 see specially page 7 and 8, claims 1,6,7,10,11,16,17,19,20, ---	1-5, 7-10,12, 13, 15-17, 19,23, 24,26,27
A	EP,A,0 396 150 (NORTON COMPANY) 7 November 1990 see the whole document see specially page 7, lines 4-10 see page 9, lines 5-15 see specially page 10, lines 45-53 ---	6,14,20, 22,28
A	WO,A,92 13680 (MINNESOTA MINING AND MANUFACTURING COMPANY) 20 August 1992 see the whole document ---	6,20
A	EP,A,0 358 383 (MINNESOTA MINING AND MANUFACTURING COMPANY) 14 March 1990 see the whole document ---	1-5,12, 15-17, 21,23, 24,26
A	DATABASE WPI Section Ch, Week 7851 Derwent Publications Ltd., London, GB; Class ALP, AN 78-92273A (51) XP002011286 & JP,A,53 131 595 (KANSAI PAINT CO. LTD. AND NIPPON ELECTROURE K.K.) , 16 November 1978 see abstract ---	1,15,16, 21
A	DATABASE WPI Section Ch, Week 9107 Derwent Publications Ltd., London, GB; Class AP, AN 91-049654 (07) XP002011287 & SU,A,1 570 891 (UKR. POLYGRAPH INST.) , 15 June 1990 see abstract -----	1,15,16, 21

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. Application No
PCT/US 96/06198

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9404318	03-03-94	US-A- 5344688	06-09-94
		AU-B- 4668793	15-03-94
		CA-A- 2140922	20-02-94
		EP-A- 0656822	14-06-95
		JP-T- 8500536	23-01-96
		US-A- 5490878	13-02-96

GB-A-2087263	26-05-82	US-A- 4457766	03-07-84
		CA-A- 1186276	30-04-85
		DE-A- 3139813	24-06-82
		FR-A- 2491377	09-04-82
		JP-A- 57089565	03-06-82
		US-A- 4547204	15-10-85
		US-A- 4588419	13-05-86

EP-A-396150	07-11-90	US-A- 5014468	14-05-91
		AU-B- 621741	19-03-92
		AU-B- 5450190	08-11-90
		CA-A,C 2015720	05-11-90
		JP-A- 3073276	28-03-91
		JP-B- 7080123	30-08-95

WO-A-9213680	20-08-92	US-A- 5152917	06-10-92
		AT-T- 137154	15-05-96
		AU-B- 661473	27-07-95
		AU-B- 1240392	07-09-92
		BR-A- 9205596	26-04-94
		CA-A- 2100059	07-08-92
		CN-A- 1064830	30-09-92
		CZ-A- 9301581	16-02-94
		DE-D- 69210221	30-05-96
		EP-A- 0570457	24-11-93
		ES-T- 2086731	01-07-96
		HU-A- 68648	28-07-95
		JP-T- 6505200	16-06-94
		US-A- 5304223	19-04-94
		US-A- 5378251	03-01-95

EP-A-358383	14-03-90	US-A- 4927431	22-05-90
		AU-B- 626903	13-08-92

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/06198

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-358383		AU-B- 3932889	15-03-90
		CA-A- 1294787	28-01-92
		DE-D- 68914920	01-06-94
		DE-T- 68914920	20-10-94
		JP-A- 2167673	28-06-90
